



Shakespeare

A valmont BRAND

19845 US HIGHWAY 76
NEWBERRY, SC 29108
P:800.800.9008
F:803.276.8940
www.skp-cs.com

9' DEADEND CROSSARM ASSEMBLY



MODEL—IDB108-150689

(Formerly IDB108G1248GPSG AND IDB108-180072)

Strong, Durable Composite Deadend Crossarm Assembly

Engineered for robust performance, Shakespeare fiberglass composite deadend crossarm assemblies serve as the anchoring points along transmission and distribution lines. Shakespeare crossarms are a great choice for use on composite, concrete, steel or wood utility poles. Often, composite crossarms are

- 4" x 6" x 108" Deadend Assembly
- Lightweight—Easy to Install
- Environmentally Safe
- Triple UV Protection
- Gray in Color
- Will not Rot, Splinter or Corrode
- Impervious to Insects, Woodpeckers
- Excellent Dielectric Properties
- Excellent Toughness and Impact Strength
- Standard Installation No Special Tools Needed



	ULTIMATE LOAD PER WIRE (LBS)	DEFLECTION PER 1000 (in)	WEIGHT (lbs)	GUY WIRE RATING EACH (lbs)	MOMENT OF INERTIA ABOUT THE NEUTRAL AXIS (in ⁴)	SECTION MODULUS ABOUT THE NEUTRAL AXIS (in ³)	BENDING STRESS (psi)	MOMENT @ FAILURE (in/lbs)	FLEXURAL MODULUS (psi)
2 WIRE RATING	14,625	.34"	77	35,000	28.36	9.45	66,561	628,875	3.71X10 ⁶
4 WIRE RATING	11,232	.44	77	35,000	28.36	9.45	66,561	629,000	3.71X10 ⁶

TESTING PER ASTM D8019-15



Shakespeare
A valmont BRAND

19845 US HIGHWAY 76
NEWBERRY, SC 29108
P:800.800.9008
F:803.276.8940
www.skp-cs.com

IDB108-150689 9' DEADEND CROSSARM ASSEMBLY

REFERENCE STANDARDS

ASTM A153 (Zinc Coating); ADTM D635 (Burning of Self Supporting Plastics); ASTM G154 (Operating light and water exposure apparatus for non-metallic materials); ASTM D8019-15 (Determining the full section flexural modulus and bending strength of fiber reinforced polymer crossarms assembled with center brackets).

WEATHER AND UV PROTECTION

UV inhibitors shall be added to the resin system and the outside surface of the crossarm shall be covered with a polyester surface veil to prevent fiber bloom. Also, the arm shall be coated with a minimum of 1.5 mils of UV resistant coating. Crossarms shall be tested for a minimum of 15,000 hrs. on the veil surface and 15,000 hrs. on the coated surface or a combined test of 30,000 hrs. with QUV-A per ASTM G154 with 4 hour light cycle and 4 hour humidity cycle.

FOAM FILLING

Crossarms shall be foam filled with a closed cell high density foam to prevent water ingress and must completely fill the crossarm and adhere to the inside walls.

MOUNTING BRACKET OR HARDWARE

Mounting brackets shall be manufactured from hot dipped galvanized steel using 50,000 psi steel. All bolts, nuts and other hardware to be hot dipped galvanized.

END CAPS

Crossarm shall be sealed with non-removable flush mounted endcaps. External caps are not acceptable.

MECHANICAL STRENGTHS

The ultimate strengths should be listed per ASTM D8019-15. Compressive strength in both the vertical and horizontal directions shall be a minimum of 500 psi without permanent deformation or damage to the fiber/resin matrix.

ELECTRICAL CHARACTERISTICS

Fiberglass crossarms shall have an average 60 Hz BIL of no less than 15kV/in and an average wet 60 Hz BIL of no less than 12 kV/in.

IDENTIFICATION

Each fiberglass crossarm shall be permanently marked with the manufacturer's name or logo and the date of manufacture

PACKAGING

Fiberglass crossarm shall be shipped fully assembled.

